1280ºC without soak

Add 3% Bentonite to this one and line blend flint into these to see whether it makes a difference to crazing.

(WK/L4) Basic Transparent Glaze 2			**ox/red**	**~1280**
Add 3% Bentonite otherwise they settle out to rock hard.	Nepheline Syenite	85		
	Whiting	15		

(WK/L5) Basic Transparent Glaze 3			**ox/red**	**~1280**
Glaze #2 & #3 give a 'cleaner' purer glaze. Add 2% flint to expand glazes and avoid crazing.	Potash Feldspar	85		
	Whiting	15		